



Photoluminescent PVC rigid sheet

Model	Thickness (mm)	Size	AFTERGLOW INTENSITY (mcd/m ²)		Appearance (Daytime)	Glowing color
			10 min	60min		
PLE-PVC-Z-G100	1.1	1m X 1.2m Or 0.5mX0.6 m	>100	>12	 Light-yellow	 Yellow-green
PLE-PVC-Z-G150	1.2		>150	>20		
PLE-PVC-Z-G200	1.2		>210	>30		
PLE-PVC-Z-G300	1.3		>300	>35		
PLE-PVC-Z-G500	1.6		>500	>68		
PLE-PVC-Z-G700	1.5		>700	>90		
PLE-PVC-M-B200	1.2		170	15		



1. The afterglow brightness is measured under D65 standard light source after being excited for 5 min by 1000 LUX.

2. Special size or thickness of photoluminescent PVC rigid sheet can be processed based on customers' requirement.

3. We can make translucent Photoluminescent PVC sheet based on customers' requirement.

4. We can add self-adhesive of the PL PVC rigid sheet based on customers' requirement (The price add 4USD/SQM).

Photoluminescent PET rigid sheet (self-adhesive)

Model	Thickness (mm)	Size	AFTERGLOW INTENSITY (mcd/m ²)		Appearance (Daytime)	Glowing color
			10 min	60min		
PLE-PET-Z-GP100	1.0~1.1	1.02m X 1.22m	>100	>12	 Light-yellow	 Yellow-green
PLE-PET-Z-GP150	1.0~1.1		>150	>20		
PLE-PET-Z-GP200	1.05~1.15		>210	>30		
PLE-PET-Z-GP300	1.1~1.2		>300	>35		
PLE-PET-Z-GP1000Y	1.9~2.1	0.61*0.91M	>980	>110		
			*>210	*>50		

1. The afterglow brightness is measured under D65 standard light source after being excited for 5 min by 1000 LUX. (**)

3000k light source after being excited for 60 min by 54LUX)

2. Thickness not include the glue, the adhesive layer thickness 0.4mm.

3. Standard product is matte surface, we can make Smooth surface based on customers' requirement



Email: info@pleu.cz

Tel: +420 728 776 110

Web: www.photoluminescent.com
